



SAFFRON GROUP

Q TR-131 - Linear Low Density Polyethylene

Product Specification

DESCRIPTION

This high molecular weight hexene copolymer provides:

- Excellent overall balance of toughness
- Good impact strength and tear properties

This resin meets these specification:

- FDA Regulation 21CFR 177.1520.
- Suitable for food packaging

It is ideal for fabricating into:

- Produce bags
- Shopping bags
- Trash bags

NOMINAL PHYSICAL PROPERTIES	ASTM	UNIT	VALUE
Density	D1505	g/cm ³	0.938
Melt Index, Condition 190°C/2.16 kg HLMI, Condition 190°C/21.6 kg	D1238 D1238	g/10min g/10min	0.2 15
Flexural Modulus, Tangent	D790	Mpa	760
Brittleness Temperature	D746	°C	<-75
Typical Film Properties* Dart Drop (66cm)	D1709	g	165
Spencer Impact Strength	D3420	J	0.35
Tensile Yield Strength, 50 mm/min	D882	MPa	MD: 21 TD: 23
Elongation at Break, 50 mm/min	D882	%	MD: 500 TD: 660
Elmendorf Tear Strength	D1922	g	MD: 30 TD: 350

*Based on 0.025 mm film produced at 4:1 blow-up ratio.

Technical Disclaimer

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes. Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to, the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself. The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg

Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • info@saffron-group.com • www.saffron-group.com