



SAFFRON GROUP

Q 3802 - Medium Density Polythylene

Product Specification

DESCRIPTION AND USE

This natural high molecular weight hexene copolymer provides:

- Excellent processability
- Exceptional melt strength
- Excellent stress cracking resistance

Typical applications include:

- PE 80 pressure pipe and fitting described in ISO standards, such as ISO 4427
- PE - Al - PE composite pipe and geomembrane

This resin meets these specifications:

- FDA Regulation 21CFR 177.1520. Suitable for food packaging
- Listed in PPI's TR - 4 as a PE 80 material

NOMINAL PHYSICAL PROPERTIES	ASTM	UNIT	VALUE
Density	D1505	g/cm ³	0.938
Melt Index, Condition 190 °C/2.16 kg	D1238	g/10min	0.20
Condition 190 °C/21.6 kg	D1238	g/10min	15
ESCR, Condition B, F50 (10% Igepal)	D1693	h	>1000
Tensile Yield Strength, 50mm/min	D638	Mpa	19
Elongation at Break, 50mm/min	D638	%	>600
Brittleness Temperature	D746	°C	<-75
Flexural Modulus, Tangent	D790	MPa	760

Technical Disclaimer

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes. Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to, the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself. The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg

Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • info@saffron-group.com • www.saffron-group.com