



## SAFFRON GROUP

# Polystyrene Crystal 1450N

## Product Specification

### DESCRIPTION

Polystyrene Crystal 1450N is a high heat resistance, easy flowing crystal polystyrene for the production of insulation board by direct gassing process. The low viscosity of this grade makes it particularly suitable for the production of insulation board at high thicknesses combining low density with good mechanical properties. This grade is not lubricated.

### APPLICATIONS

Insulation board, XPS.

### PROPERTIES

RHEOLOGICAL	METHOD	UNIT	VALUE
Melt flow index (200°C-5kg)	ISO 1133 H	g/10mn	6.5
THERMAL			
Vicat softening point 10N (T° increase = 50°C/h)	ISO 306A50	°C	105
Vicat softening point 50N (T° increase = 50°C/h)	ISO 306B50	°C	101
HDT unannealed under 1.8MPa	ISO 75-2A	°C	84
HDT annealed under 1.8MPa	ISO 75-2A	°C	99
Coefficient of linear thermal expansion		mm/°C	7.10 E-5
MECHANICAL			
Notched Charpy impact strength	ISO 179/1eA	KJ/m2	8
Tensile strength at break	ISO 527-2	Mpa	48
Elongation at Break	ISO 527-2	%	3
Tensile modulus	ISO 527-2	Mpa	3200
Flexural modulus	ISO 178	Mpa	2900
Rockwell hardness	ISO 2039-2		L70

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg

Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • [info@saffron-group.com](mailto:info@saffron-group.com) • [www.saffron-group.com](http://www.saffron-group.com)



# SAFFRON GROUP

ELECTRICAL			
Dielectric strength		kV/mm	135
Surface resistivity	ISO IEC 93	Ohms	>10 E+14
MISCELLANEOUS			
Density	ISO 1183	g/cm <sup>3</sup>	1.05
Moulding shrinkage		%	0.4-0.7
Water absorption	ISO 62	%	<0.1

## GENERAL INFORMATION

- Standard properties: All tests carried out at 23°C unless otherwise stated. Mechanical properties are measured on injection moulded test specimens.
- Bulk density: bulk density is approximately 0.6 g/cm<sup>3</sup>.
- Please refer to the Safety Data Sheet for further information.
- Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within six months after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: [www.totalreningchemicals.com](http://www.totalreningchemicals.com)

## Technical Disclaimer

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes. Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to, the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself. The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg  
Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • [info@saffron-group.com](mailto:info@saffron-group.com) • [www.saffron-group.com](http://www.saffron-group.com)