



## SAFFRON GROUP

# Polystyrene Impact 8260

## Product Specification

### DESCRIPTION

Polystyrene Impact 8260 is an high impact polystyrene for extrusion and injection applications.

This grade has an improved environmental stress crack resistance in comparison with standard high impact grades. The product has been specially designed for the production of refrigerator part: inner liners, door liners, injected parts, etc.

This grade is also proposed for the production of packaging intended for products likely to cause stress cracking e.g. fats, oil.

Polystyrene Impact 8260 retains good mechanical properties at low temperatures making this grade suitable for frozen packaging; it also affords good printing performance.

### APPLICATIONS

Sheet for thermoforming, fridges liners, low temperature packaging applications (ice cream boxes and lids), packaging for aggressive foodstuffs, matt finish, soft touch.

### PROPERTIES

RHEOLOGICAL	METHOD	UNIT	VALUE
Melt flow index (200°C-5kg)	ISO 1133 H	g/10mn	2.8
THERMAL			
Vicat softening point 10N (T° increase = 50°C/h)	ISO 306A50	°C	99
Vicat softening point 50N (T° increase = 50°C/h)	ISO 306B50	°C	90
Coefficient of linear thermal expansion		mm/°C	9.10 E-5
MECHANICAL			
Notched Charpy impact strength	ISO 179/1eA	KJ/m2	11
Notched Izod impact strength	ISO 180/1A	KJ/m2	11
Tensile strength at yield	ISO 527-2	Mpa	20
Tensile strength at break	ISO 527-2	Mpa	25
Elongation at Break	ISO 527-2	%	>60
Tensile modulus	ISO 527-2	Mpa	1600
Flexural modulus	ISO 178	Mpa	1600

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg

Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • [info@saffron-group.com](mailto:info@saffron-group.com) • [www.saffron-group.com](http://www.saffron-group.com)



# SAFFRON GROUP

ELECTRICAL			
Dielectric strength		kV/mm	150
Surface resistivity	ISO IEC 93	Ohms	>10 E+13
MISCELLANEOUS			
Density	ISO 1183	g/cm <sup>3</sup>	1.04
Moulding shrinkage		%	0.4-0.7
Water absorption	ISO 62	%	<0.1

## GENERAL INFORMATION

- Standard properties: All tests carried out at 23°C unless otherwise stated. Mechanical properties are measured on injection moulded tests specimens.
- Bulk density: bulk density is approximately 0.6 g/cm<sup>3</sup>.
- Please refer to the Safety Data Sheet for further information.
- Please refer to the safety data sheet (MSDS) for handling and storage information. It is advisable to convert the product within six months after delivery provided storage conditions are used as given in the MSDS of our product.

## Technical Disclaimer

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes. Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to, the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself. The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.

FOR MORE INFORMATION :

SAFFRON GROUP • Georg-Wilhelm-Str. 181 • D-21107 Hamburg  
Fon +49 (0) 40 55435542-0 • Fax +49 (0) 40 55435542-9 • [info@saffron-group.com](mailto:info@saffron-group.com) • [www.saffron-group.com](http://www.saffron-group.com)